



Curax MF

Metallic salt-free self-shine dispersion

Packaging	Art.-No.	Per Box	Per Pallet
10 l PE-canister	6326	-	60

Properties: Curax MF is a wax based PE-dispersion without metallions for environmentally friendly floor care. Curax MF dries streak-free and self-shining. The resulting anti-slip film can be polished by using a slow rotating single disc machine as well as using a high speed-machine. Gloss and durability increase with higher engine speed. The floor polish is safe to walk on. The measured values of the sliding friction are above a value of 0,4 (measured by using a Floor slide control FSC 2000). Even by polishing the film this value of 0,4 will not fall below. As a result the values for the sliding friction correspond to Norm DIN 18032. Footmarks can be polished out. Deep scratches will be repaired by the so-called „cleaner-process“. Runs or spurs on the floor are repaired with Curax MF diluted 1: 1 with water. By renewing the floor polish/coating after an intermediate cleaning process by applying Curax MF once again, a costly basic cleaning can be avoided.

Field of Application: Suitable for the use on waterproofed, hard and elastic floor coverings: PVC, linoleum, rubber, sealed wooden floors, stone floors. For the use on polyolefin-floors first check the adhesion by testing.

Application: Before applying Curax MF for the first time on the floor, basic cleaning and complete drying of the floor is necessary. Apply Curax MF undiluted with suitable device onto the correctly prepared flooring and leave to dry. Carry out two to three applications. For application a lambswool wiper or a not too wide, flat mop have proven themselves. Curax MF gives gloss after applying. Gloss can be increased by polishing. Polishing may not take place until after the hardening time of at least three days (eg. with a single disc machine and a white pad). The scratches and traces arising during use of the flooring can be polished out. Larger traces and spurs occurring during using the floor can be repaired with Curax MF by using 2 methods: 1) Partially: After an intermediate cleaning Curax MF is applied undiluted or 1:1 with water and is polished after the drying process. 2) After using the floor for a long time it is recommendable, for example once a year, to refresh the whole polish. After an intermediate cleaning Curax MF is applied undiluted to 1:1 with water. For using Curax MF in a spray-cleaning process use Curax MF in dilution 1:10 with.


Dosage: Undiluted.

Consumption: Performance: 10 l for ca. 400 m² per application. Depending on absorbency of the flooring different values are possible. Porous surfaces: 10 l for ca. 150 bis 300 m² per application.

Ingredients: <5% nonionic surfactants, <5% anionic surfactants, Benzisothiazolinone, Methylisothiazolinone, Polyacrylates, PE-Waxes, additives.

Productcode: GE 10

This product is intended for commercial use only. Safety data sheet available on request or at www.fala.de. For safety instructions pay attention to product label or safety data sheet.




Manual processing,
apply evenly



Polishable with
single disc machine



Spray cleaning
possible



Apply undiluted